



DIPS Size	Avg. OD	SDR PSI	7 335	9 250	11 200	13.5 160	17 130	21 100	26 80	32.5 65
4	4.80	Min Wall	.686	.533	.436	.356	.282	.229	.185	.148
		Avg ID	3.346	3.67	3.876	4.045	.4202	4.315	4.408	4.487
		Weight p/ft	3.87	3.13	2.62	2.18	1.76	1.44	1.18	.95
6	6.90	Min Wall	.986	.767	.627	.511	.406	.329	.265	.212
		Avg ID	4.81	5.274	5.571	5.817	6.039	6.203	6.338	6.45
		Weight p/ft	8	6.47	5.42	4.5	3.64	2.98	2.43	1.96
8	9.05	Min Wall	1.293	1.006	.823	.67	.532	.431	.348	.278
		Avg ID	6.309	6.917	7.305	7.63	7.922	8.136	8.312	8.46
		Weight p/ft	13.76	11.13	9.32	7.75	6.26	5.13	4.19	3.38
10	11.10	Min Wall	1.586	1.233	1.009	.822	.653	.529	.427	.342
		Avg ID	7.738	8.486	8.961	9.357	9.716	9.97	10.195	10.376
		Weight p/ft	20.7	16.74	14.03	11.66	9.42	7.72	6.3	5.08
12	13.20	Min Wall	1.886	1.467	1.2	.978	.776	.629	.508	.405
		Avg ID	9.202	10.09	10.656	11.127	11.555	11.867	12.123	12.339
		Weight p/ft	29.27	23.67	19.84	16.48	13.32	10.92	8.91	7.19
14	15.30	Min Wall	2.186	1.7	1.391	1.133	.9	.729	.588	.471
		Avg ID	10.666	11.696	12.351	12.898	13.392	13.755	14.053	14.302
		Weight p/ft	39.33	31.8	26.65	22.15	17.89	14.67	11.97	9.66
16	17.40	Min Wall	2.486	1.933	1.582	1.289	1.024	.829	.669	.535
		Avg ID	12.13	13.302	14.046	14.667	15.229	15.643	15.982	16.265
		Weight p/ft	50.87	41.13	34.47	28.64	23.14	18.97	15.48	12.49

United Poly Systems Pressure Pipe is manufactured to the following standards:
 ASTM D3035, AWWA C901/C906, F714, D2513, NSF 61

4707 E. Kearney St., Springfield, MO 65803 phone: 417.708.9887 fax: 877.630.8693 www.unitedpolysystems.com